



CHOCOLATE ARIZONA sandstone

Absorption by weight (%)	3.1
Density (lbs/ft ³)	147.9
Modulus of Rupture (psi)	na
Compressive Strength (psi)	11,900
Abrasion Resistance	na
Hardness	na
Flexural Strength (psi)	na
Coeff. Thermal Expansion	na

Absorption by weight (%)	
Specific Gravity (kg/m ³)	
Modulus of Rupture (MPa)	
Compressive Strength (MPa)	
Abrasion Resistance (mm)	
Flexural Strength (MPa)	
Coeff. Thermal Exp. (per °C x 10 ⁻⁶)	