

KGGO

A NATURAL STONE COMPANY

PHONE 360-606-2205
FAX 360-687-1449
info@kgostone.com
www.KGOSTone.com

BERKSHIRE™ LIMESTONE VENEER

Berkshire

Made of the same high quality raw material used in our nation's most renowned buildings.

Berkshire (historically known as Bedford Stone) split face full color blend Indiana Limestone exhibits naturally subtle color and grain variations.

Berkshire/Bedford Stone adds permanence and lasting value to any commercial or residential project.



Properties of Indiana Limestone

Most building designs that incorporate Indiana Limestone consider these properties:

- Ultimate compressive strength of dry specimens

Value: 4,000 psi min.* Test STD: ASTM C170

- Modulus of rupture of dry specimens

Value: 700 psi min.** Test STD: ASTM C99

- Absorption

Value: 7.5 % max. Test STD: ASTM C97

*Most Indiana Limestone products indicate min. values in excess of 4,000 psi, but this value is listed as an engineering reference.

**Windload and other bending forces are typically calculated at 1,000 psi for modulus of rupture.

NOTE: All Indiana Limestone meets or exceeds the strength requirements set forth in ASTM C-568 for Type II Dimension Limestone.

- Abrasion Resistance

When used in flooring, paving, or steps, the abrasion resistance should be specified.

- Value Range: (Abrasive Hardness)

6 min. to 17 max.† Test STD: ASTM C241

†Stone preparation and installation details are important in assuring hardness of 8 for heavy traffic areas. Specify abrasive hard-